

**Nurcagran IS60-75****Predispersed Rubber  
Chemicals and Additives****Code:** IS60-75GE F500**PRODUCT SPECIFICATIONS**

Appearance: yellow granule

Sulfur content: (%) 73.0-77.0

Insoluble sulfur: (%) 43.0-51.0

Density at 20°C: (g/cm<sup>3</sup>) 1.32-1.42

Mooney, ML (1+4) 50°C: 30.0-60.0

Ash (950°C, 2h): (%) max. 5.0

Filtration: (μm) 500

Binder Content (EPDM/EVM): (%) 25

**PACKAGING:**PE bag lined, 25kg (net) per carton.  
600kg per pallet. Do not pile more than 2 pallets height.**Shelf Life:**

In original closed containers under cool and dry conditions, avoid direct sunlight. max. 1 year from production date.